

SIMRIZ® 484

SIMRIZ® 484 FOR FOOD & BEVERAGE APPLICATIONS




Designed for thermal stability and nearly universal protection against chemical attack, Freudenberg's proprietary family of Simriz® perfluoroelastomer compounds offer premier sealing performance. Simriz® compounds approach PTFE chemical resistance while resisting high temperatures up to 325°C.

Freudenberg is the only vertically integrated supplier of perfluoroelastomer.

Traceable - Accountable – Customized - Controlled.

Simriz® 484 performs well in a wide variety of harsh chemicals as well as at high temperatures. Also Simriz® 484 is FDA compliant and USP class VI compliant, making it the perfect match for any Food & Beverage and Pharmaceutical application.

Change in Hardness Steam 72h / 200 °C (392 °F)



VALUES FOR THE CUSTOMER

- Broad chemical resistance in a large number of harsh chemical environments (e.g. CIP/SIP media)
- Low compression set resulting in an increased product life time
- FDA compliant
- USP class VI compliant
- Meets 3-A® Sanitary Standards
- ADI free
- Without equal. Patented cross-linking system provides superior performance beyond the limits of every other competitor FFKM product
- Demonstrated performance. Successfully used in many customer applications
- Vertically integrated. Freudenberg Sealing Technologies is the only vertically integrated O-ring manufacturer in the world
- Cost efficient. As the only vertically integrated O-ring manufacturer down to the monomers Freudenberg Sealing Technologies is able to provide the most cost efficient FFKM O-rings

TYPICAL APPLICATIONS

- CIP / SIP Equipment
- Pumps
- Valves
- Mechanical Seals
- Dispenser Systems
- Mixers

FEATURES AND BENEFITS

Mechanical Properties	
Hardness (Shore) DIN ISO 7619-1, Shore A, 23 °C	75
Temp. Range in °C	-20 °C to +230 °C
Temp. Range in °F	-4 °F to +446 °F
Tensile Strength (psi)	3205
Tensile Strength (MPa)	22.1
Elongation (%)	165
Compression Set (%) 70hr at 204 °C (400 °F) per ASTM D395 - Method B	33

Chemical Environment	
Hot Water / Steam	++
Dry Heat	+
Organic Acid (e.g. Acetic Acid)	+
Inorganic Acids (e.g. Nitric Acid)	+
Alkalis / Bases	++
Acrylic or Vinyl Monomers	++
Amines	++
Hot Amines	++
Ketones	++
Ester	++
Ethers	++
Aldehydes	++
Hydrocarbons	++
Sour Gas (e.g. Hydrogen Sulfide, Peroxide)	++
Silanes and Chlorosilanes	++
Hot Lubricants	++
Strong Oxidizers (e.g. Nitric Acid, O ₃ , ClO ₃) -	-
Fluorinated Fluids	++
Synthetic Oils	++
Alcohols	++

The information contained herein is believed to be reliable, but no representations, warranties or guarantees of any kind are made as to its accuracy or suitability for any purpose. The information reproduced herein is based on laboratory testing and is not necessarily indicative of the performance of the final product. The user is responsible for performing complete testing and for the performance of the final product.

www.fst.com