



MATERIAL REPORT

REPORT NUMBER: DD4005
DATE: 02/13/90

TITLE: Evaluation of Low Temperature Parker Compound S0383-70 to ZZ-R-765C Class 2A Grade 70
PURPOSE: To determine if S0383-70 meets the requirements.
CONCLUSION: Compound S0383-70 meets the requirements.

Recommended temperature limits: -175⁰F to 400⁰F

Recommended For

Dry heat
Some petroleum oils
Moderate water resistance
Fire resistant hydraulic fluids (HFD-R and HFD-S)
Ozone, aging, and weather resistance
Extreme Low temperature

Not Recommended For

Ketones
Acids
Silicone oils
Auto and aircraft brake fluid



Contact Us



REPORT DATA

Report Number: DD4005

	ZZ-R-765C Class 2A Pass / Fail Limits	S0383-70 Slab Results
<u>Basic Physical Properties</u>		
Hardness	70 +/- 5	67
Tensile Strength, psi	650	1240
Elongation, %	125	242
Modulus @ 100%, psi	NR	669
Specific Gravity	NR	1.27
<u>ASTM D573 Heat Aging, 70 H @ 437°F</u>		
Hardness Change, pts	+/-10	+5
Tensile Change, % max	-20	-5
Elongation Change, % max	-40	-19
<u>Compression Set,</u> <u>70 HRS @ 302°F</u>		
% of Original Deflection, max	40	15
<u>Fluid Immersion, ASTM #1 Oil,</u> <u>70 H @ 302°F</u>		
Hardness Change, pts	-15 to +5	-9
Tensile Change, % max	-20	-3
Elongation Change, % max	-15	-1
Volume Change, % max	+15	+9
<u>Low Temp Brittleness ASTM D2137 Method A</u> <u>3 MIN @ -80°F</u>	Pass	Pass



Contact Us

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40509
(859) 269-2351